

AMENDMENTS TO THE CLAIMS

1. (Previously presented) A thermoplastic molding composition, comprising a mixture of
 - (A) from 30 to 69% by weight, based on the sum of components (A), (B) and (C), of a methyl methacrylate polymer obtainable by polymerizing a mixture consisting of
 - (A1) from 90 to 100% by weight, based on (A), of methyl methacrylate, and
 - (A2) from 0 to 10% by weight, based on (A), of a C₁–C₈–alkyl ester of acrylic acid, and
 - (B) from 30 to 69% by weight, based on the sum of components (A), (B) and (C), of a copolymer obtainable by polymerizing a mixture consisting of
 - (B1) from 75 to 88% by weight, based on (B), of a styrenic monomer and
 - (B2) from 12 to 25% by weight, based on (B), of a vinyl cyanideand
 - (C) from 1 to 40% by weight, based on the sum of components (A), (B) and (C), of a graft copolymer obtainable from
 - (C1) from 60 to 90% by weight, based on (C), of a core obtainable by polymerizing a monomer mixture consisting of
 - (C11) from 65 to 90% by weight, based on (C1), of a 1,3–diene and
 - (C12) from 10 to 35% by weight, based on (C1), of a styrenic monomer
 - (C2) from 5 to 20% by weight, based on (C), of a first graft shell and
 - (C3) from 5 to 20% by weight, based on (C), of a second graft shell obtainable by polymerizing a monomer mixture consisting of
 - (C31) from 70 to 98% by weight, based on (C3), of a C₁–C₈–alkyl ester of methacrylic acid and

(C32) from 2 to 30% by weight, based on (C3), of a C₁-C₈-alkyl ester of acrylic acid

and

(D) optionally, customary additives in amounts of up to 20% by weight, based on the sum of components (A), (B) and (C),

with the proviso that the weight ratio of (C2) to (C3) is in the range from 2:1 to 1:2,

wherein the first graft shell (C2) is obtainable by polymerizing a monomer mixture consisting of

(C21) from 30 to 35% by weight, based on (C2), of a styrenic monomer,

(C22) from 63 to 70% by weight, based on (C2), of a C₁-C₈-alkyl ester of methacrylic acid and

(C23) from 0 to 2% by weight, based on (C2), of a crosslinking monomer.

2. (Previously presented) The thermoplastic molding composition according to claim 1, wherein the refractive index (n_D-C_2) of the first graft shell (C2) is greater than the refractive index (n_D-C_3) of the second graft shell (C3), and the refractive index ($n_D-C_2C_3$) of the overall graft shell is less than the refractive index (n_D-C_1) of the core (C1), and the magnitude of the difference of the refractive index (n_D-C) of the overall component (C) and the refractive index (n_D-AB) of the overall matrix of components (A) and (B) is less than or equal to 0.02.

3. (Cancelled).

4. (Previously Presented) The thermoplastic molding composition according to claim 1, wherein the first graft shell (C2) is obtainable by polymerizing a monomer mixture consisting of

(C21) from 31 to 35% by weight, based on (C2), of a styrenic monomer,

(C22) from 63 to 68% by weight, based on (C2), of a C₁-C₈-alkyl ester of

methacrylic acid and

(C23) from 1 to 2% by weight, based on (C2), of a crosslinking monomer.

5. (Previously presented) The thermoplastic molding composition according to claim 1, wherein the magnitude of the difference between the refractive index ($n_D-C_2C_3$) of the overall graft shell of the graft copolymer C and the refractive index (n_D-C_1) of the core (C1) is less than 0.06.

6. (Previously Presented) The thermoplastic molding composition according to claim 1, wherein the styrenic monomer used is styrene.

7. (Previously presented) The thermoplastic molding composition according to claim 1, wherein the graft copolymer (C) has a swelling index SI of from 10 to 40.

8. (Currently Amended) A process for producing thermoplastic molding compositions according to claim 1, which comprises

(A) from 30 to 69% by weight, based on the sum of components (A), (B) and (C), of a methyl methacrylate polymer obtainable by polymerizing a mixture consisting of

(A1) from 90 to 100% by weight, based on (A), of methyl methacrylate, and

(A2) from 0 to 10% by weight, based on (A), of a C_1-C_8 -alkyl ester of acrylic acid, and

(B) from 30 to 69% by weight, based on the sum of components (A), (B) and (C), of a copolymer obtainable by polymerizing a mixture consisting of

(B1) from 75 to 88% by weight, based on (B), of a styrenic monomer and

(B2) from 12 to 25% by weight, based on (B), of a vinyl cyanide

and

(C) from 1 to 40% by weight, based on the sum of components (A), (B) and (C), of a graft copolymer obtainable from

(C1) from 60 to 90% by weight, based on (C), of a core obtainable by

polymerizing a monomer mixture consisting of

(C11) from 65 to 90% by weight, based on (C1), of a 1,3-diene and

(C12) from 10 to 35% by weight, based on (C1), of a styrenic monomer

and

(C2) from 5 to 20% by weight, based on (C), of a first graft shell obtainable by
polymerizing a monomer mixture consisting of

~~(C21) from 30 to 39% by weight, based on (C2), of a styrenic monomer,~~

~~(C22) from 61 to 70% by weight, based on (C2), of a C₁-C₈-alkyl ester~~

~~of methacrylic acid and~~

~~(C23) from 0 to 3% by weight, based on (C2), of a crosslinking monomer~~

~~(C21) from 30 to 35% by weight, based on (C2), of a styrenic monomer,~~

~~(C22) from 63 to 70% by weight, based on (C2), of a C₁-C₈-alkyl ester~~

~~of methacrylic acid and~~

~~(C23) from 0 to 2% by weight, based on (C2), of a crosslinking monomer~~

and

(C3) from 5 to 20% by weight, based on (C), of a second graft shell obtainable by
polymerizing a monomer mixture consisting of

(C31) from 70 to 98% by weight, based on (C3), of a C₁-C₈-alkyl ester of

methacrylic acid and

(C32) from 2 to 30% by weight, based on (C3), of a C₁-C₈-alkyl ester of

acrylic acid

and

(D) optionally, customary additives in amounts of up to 20% by weight, based on the
sum of components (A), (B) and (C),

with the proviso that the weight ratio of (C2) to (C3) is in the range from 2:1 to 1:2,

by mixing components (A), (B), (C) and, where present, (D) in the melt.

9. (Cancelled).
10. (Previously Presented) A molding comprising the thermoplastic molding composition according to claim 1.
11. (Cancelled).
12. (Original) The thermoplastic molding composition according to claim 2, wherein the first graft shell (C2) is obtainable by polymerizing a monomer mixture consisting of
 - (C21) from 31 to 35% by weight, based on (C2), of a styrenic monomer,
 - (C22) from 63 to 68% by weight, based on (C2), of a C₁–C₈–alkyl ester of methacrylic acid and
 - (C23) from 1 to 2% by weight, based on (C2), of a crosslinking monomer.
13. (Cancelled).
14. (Previously presented) The thermoplastic molding composition according to claim 2, wherein the magnitude of the difference between the refractive index (n_D –C₂C₃) of the overall graft shell of the graft copolymer C and the refractive index (n_D –C₁) of the core (C1) is less than 0.06.
15. (Cancelled).
16. (Previously presented) The thermoplastic molding composition according to claim 4, wherein the magnitude of the difference between the refractive index (n_D –C₂C₃) of the overall graft shell of the graft copolymer C and the refractive index (n_D –C₁) of the core (C1) is less than 0.06.
17. (Original) The thermoplastic molding composition according to claim 2, wherein the styrenic monomer used is styrene.

18. (Cancelled).

19. (Original) The thermoplastic molding composition according to claim 4, wherein the styrenic monomer used is styrene.

20. (Original) The thermoplastic molding composition according to claim 5, wherein the styrenic monomer used is styrene.